

Blackhawk R-17-A-73 Asphalt Coating/Primer ANSI/NSF61 approved

Product Information Sheet

SELECTION & SPECIFICATION DATA

Description Blackhawk R-17-A-73 Asphalt Coating/Primer is an ANSI/NSF61 approved, quick-dry black asphaltic glossy coating that can be universally used for the outside and inside of ductile iron pipe and fittings, including for potable applications. It is a convenient solution for touchup and re-coating applications.

Features BH Aerosol Coating/Primer is a penetrating and sealing primer. It helps subsequent asphalt coatings, asphalt, or butyl peel and stick products bond.

Recommended Uses BH Aerosol Coating/Primer can be used on metal as basic corrosion protection in automotive applications and also as a roofing primer. It can also be used as a touch up for other asphalt based coatings.

- Color: Black
- Topcoats: Asphalt only
- Finish: Gloss
- Dry Film Thickness: 1 – 2 mils DFT
- Solids Content: 55 +/- 3%
- Theoretical Coverage Rate: 33-45 square feet per can
- VOC Value(s): > 450 g/l

SUBSTRATES & SURFACE PREPARATION

General: All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.

CLEANUP & SAFETY

Cleanup: Use mineral spirits for suitable cleanup. In case of spillage absorb and dispose of in accordance with local applicable regulations. Refer to SDS for more information.

Safety: Read and follow all caution statements on this product data sheet and on the SDS for this product. Wear protective clothing, gloves and eye protection.

Ventilation: Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.



PACKAGING, HANDLING & STORAGE

Shelf Life: 12 months at 75°F (24°C)
When kept at recommended storage conditions and in original unopened containers.

Shipping Weight: 24 lbs per case of 12 cans

Storage Temperature: 40° - 110°F (4° - 43°C)

Storage Humidity: 0-100% Relative Humidity

Storage: Store Indoors. This product is not affected by excursions below these published temperatures, down to 10°F, for a duration of no more than 14-days. Always inspect the product prior to use to make sure it is smooth and homogenous and properly mixed.